S<sub>4</sub>a

10/2011

## Repair System for new e-coated parts

Properties: Economical repair process for time-saving, low-cost refinishing of e-coated parts without sanding.

Considerable time is saved by a wet-on-wet application of Glasurit® 285-31, 285-38, 285-49 Non-Sanding

Filler.

Remarks: New E-coated parts have to be protected from sun light; because there is a risk of loose adhesion and

corrosion protection.

Cleaning

541-5 Glasurit® Wax and Silicone Remover





Fillers and Surfacers

285-31 Glasurit® HS Non-Sanding Filler light grey 929-55, -56 Glasurit® HS Primer Hardener 352-Glasurit® Reducer 3:1:1 HV mixing stick 2 0.3

HVLP 1.3 mm 2.0-3.0 bar 1 - 2 20-35 µm

10 -20 min at 20°C

or alternatively:

Glasurit® 285-38, 285-49 HS Non-Sanding Filler

**Topcoats** 

22 Line Glasurit® HS 2K Topcoat VOC 90 Line Glasurit® Basecoat 923-Glasurit® Clear VOC

## Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1  $\mu m$ .

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at http://lechinfo.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

