

90

90 Line Variant Mixed Tinters



A brand of BASF –
We create chemistry

Application: Mixture of 90 Line mixed tinters without 90-M 4 Waterborne Mixing Base (e. g. at colour TOY 8Y0). Please observe the mixing ratio on the label.
Mixture will keep for 24 months when stored in closed plastic containers or cans coated inside.
Potlife RFU: 1 week in a sealed plastic vessel.



Spreading rate 130 m²/l at 1 µm

Handling



Premix:
70 % by weight 90-M 4
30 % by weight 90 Line mixed tinters (stir after addition of product)

2:1



Mixing Ratio 100 % by volume 90 Line (mixture of 90 Line Waterborne Mixing Base / 90 Line mixed tinters)



Reducer 50 % by volume 93-E 3
Stir IMMEDIATELY after having added adjusting base.
When using 90-M 4 slow in the PreMix 93-E 3 slow must also be used.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.



The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

90

90 Line Variant Mixed Tinters



A brand of BASF –
We create chemistry

Application:	 Compliant gravity-feed spray gun	 HVLP spray gun
Application pressure	2 bar	2-3 bar
Nozzle pressure		0.7 bar
Nozzle size	1.3-1.4	1.3
Number of spray coats	2 (spray to cover) + ½ to match the effect	
Flash off at 20°C	Approx. 5 min. after each spraycoat.	
Film thickness	10-15 µm	



Sanding manual, dry

Remove dust nibs by dry sanding; gently fade out applying mist coat afterwards.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.