

Glasurit® HS VOC Non-Sanding Filler, light grey

G / F

- Application:** Wet-on-wet surfacer for economical repairs
- Properties:** No sanding and no drying times; very safe to spray; good finish, good weathering resistance
- Remarks:**
- Before filler application: fine sand body-filled areas and old paintwork with P320 (dry). Use 581-90 Guide Coat.
 - No need to sand new e-coated parts
 - Prime sand-throughs with 283-150 Glasurit® etch primer filler.
 - If mixed with 522-10 Glasurit Plastic Additive, the product can be used on all coatable plastics that are commonly used in the automotive industry.
 - Parts coated with 285-31 can be overcoated without intermediate sanding for up to 5 days

	Paint system	S 4		
				Spreading rate: 331 m ² /l at 1 µm
	Mixing ratio	3 : 1 : 1 100% by vol.	285-31	
	Hardener	33% by vol.	929-56, -55	
	Reducer	33% by vol.	352-91/-216 352-30, -40	
	Spray viscosity DIN 4 at 20°C	16-19 s		Potlife at 20°C: 2 hours
	Gravity cup Spraying pressure	HVLP-gravity-feed spray gun: 1.3 mm 2.0 – 3.0 bar 0.7 bar at the nozzle		Compliant gravity-feed spray gun: 1.3 -1.4 mm 2.0 bar
	Number of spraycoats	2 (one on body-filled area and one on entire surface to be painted)		Film thickness: approx. 20-35 µm
	Flash-off at 20°C	10 min. solids / 15-20 min. topcoat/basecoat metallics (matt)		

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/II B(c II)(540)530: The EU limit value for this product (product category: IIB.C II) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 530 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

