## 176-72



1K Waterborne Primer Surfacer - Dark Gray, Water Dilutable - as guide coat

Application:

**Key Features:** 

Remarks:

Primer filler used as guide coat.

Contains less than 5% organic solvents.

- Minimum working temperature is 60°F/15°C.
- · Drying is strongly dependent on temperature, humidity, air circulation and film build.
- · Keep spray gun head under water when the gun is not in use.
- · Use 90-VE to clean sanding residue.
- Use 700-1 to clean spray gun and tools.
- Collect left-over paints and waste water, treat them with 700-7 Coagulating Powder and dispose of them according to the relevant technical data sheets.
- Keep product from freezing (store at temperature 40°F-105°F/5°C-40°C).
- · Shelf life 18 months.
- · Not suitable for use on flexible plastic parts.
- Do not apply 176-72 directly over or under peroxide cured body fillers or over acid containing pretreatments.

VOC ready for use		100 g/l 0.8 lb/gal	
		1:1	
	Mixing Ratio	100 parts by volume	176-72
	Reducer	100 parts by volume	93-E3
s	Spray viscosity at 68°F / 20°C	DIN 4: 25-35 s	

## Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.

## 176-72



1K Waterborne Primer Surfacer - Dark Gray, Water Dilutable - as guide coat

Application:	Compliant gravity-feed spray gun	🕌 HVLP spray gun	
Nozzle pressure		10 psi	
Nozzle size		1.6-1.8 mm	
Number of spraycoats	2		
Flash-off at 68°F / 20°C	5 min between coats and before drying or until matte		
Film thickness	1.6-2.4 mil	1.6-2.4 mil	
Application remark	(maximum nozzle pressure	(maximum nozzle pressure of 10 psi)	

Drying at 68°F / 20°C 2 h

at 50% relative humidity

Drying at 140°F / 60°C

30 min

Infrared (short wave)

3-5 min

Infrared (medium wave)

15-20 min



Sanding manual, dry

360, clean with DI water or 90-VE



Orbital sanding, dry

400 - 600, clean with DI water or 90-VE

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document

## Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.