

285-02

Low VOC Transparent Sealer - National Rule Recommendation - Tinted with 90 Line



A brand of BASF –
We create chemistry

- Application:** Wet-on-wet sealer for National Rule areas.
- Key Features:** No sanding before topcoating.
- Remarks:**
- Prime bare-metal exposure with Glasurit 283- etch primer filler, Glasurit 285-50, -60 or Glasurit 801-72.
 - Prime raw plastic exposure with plastic adhesion promoter.

VOC ready for use 520 g/l 4.3 lb/gal



Mixing Ratio 75 parts by volume 285-02



Hardener 25 parts by volume 929-51, -53



Reducer 25 parts by volume 352-50, -91, -216

Additive 10 parts by volume 90-Line



Spray viscosity at 68°F / 20°C DIN 4: 12-16 s

Potlife at 68°F / 20°C 1 h

Safety advice:



Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.

285-02

Low VOC Transparent Sealer - National Rule Recommendation - Tinted with 90 Line



A brand of BASF –
We create chemistry

Application:	 Compliant gravity-feed spray gun	 HVLP spray gun
Nozzle pressure		10 psi
Nozzle size		1.3-1.4 mm
Number of spraycoats	1-2	
Flash-off at 68°F / 20°C	5 - 10 mins. between coats 15 - 20 mins. before topcoating	
Film thickness	1-1.4 mil	



Sanding manual, dry

Dust nibs can be removed with 600 grit

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document

Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.