



A brand of BASF – We create chemistry

Application:		Primer surfacer.		
Key Features:		285-15 is an acrylic two-component surfacer designed for application on automotive substrates including CRS, aluminum and galvanized.		
Remarks:		 May be sanded in as little as 15 - 30 minutes. 		
		 285-15 may be mixed with 285-25 (White) to achieve differing L shades. 		
		522-20 Universal Rapid Additive is required.		
		 BASF 1000 wipes can be used for enhanced corrosion control. 		
		 Surface cleaning and preparation are critical to the success of the 285-15. All grease, rust and dirt must be properly removed. 		
VOC ready for use		220 g/l 1.8 lb/gal		
	Mixing Ratio	100 parts by volume	285-15	
Â	Hardener	25 parts by volume	929-385	
	Additive	12.5 parts by volume	522-20	
Ş	Spray viscosity at 68°F / 20°C	DIN 4: 16-19 s		
	Potlife at 68°F / 20°C	1 h		

Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.

285-15

Black DTM Primer Filler - Rapid Process, National Rule and Low VOC



A brand of BASF – We create chemistry

Application:	Compliant gravity-feed spray	😽 HVLP spray gun
Nozzle pressure		10 psi
Nozzle size		1.5-1.7 mm
Number of spraycoats	2-3 medium to wet	
Flash-off at 68°F / 20°C	5 min between coats	
Film thickness	3-5 mil before sanding	
Drying at 68°F / 20°C	15-30 min (Do not bake.)	
Sanding manual, wet	P320-P500	
Sanding manual, dry	P320-P500	
Orbital sanding, dry	P400-P500	

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document

Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.