285-15



Black DTM Primer filler - Rapid Process, National Rule - Flexible

Application:

Flexed primer surfacer, rapid process.

Key Features:

285-15 is an acrylic two-component surfacer which may be flexed for application on bumpers and other

flexible plastic.

Remarks:

- 285-15 may be mixed with 285-25 (White) to achieve differing L shades.
- 10% 522-111 must be added prior to hardener and reducer.
- 934-30 Adhesion Promoter must be applied to bare flexible plastic before applying primer.
- Surface cleaning and preparation are critical to the success of the 285-15. All grease, rust and dirt
 must be properly removed.

VOC ready for use		365 g/l 3.1 lb/gal	
	Mixing Ratio Pre-Mix	100 parts by volume 285	-15 -111
	Mixing Ratio	77.6 g	Pre-Mix
	Hardener	12.4 g	929-385
	Reducer	6.3 g	352-91
	Additive	3.7 g	522-20



Spray viscosity at 68°F /

20°C

DIN 4: 15-17 s

Potlife at 68°F / 20°C

2 h

Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.

285-15



Black DTM Primer filler - Rapid Process, National Rule - Flexible

Application:		Compliant gravity-feed spray	HVLP spray gun
Nozzle pressure			10 psi
Nozzle size			1.5-1.7 mm
Number of spraycoats		2-3	
Flash-off at 68°F / 20°C		5 min between coats	
Film thickness		3-5 mil before sanding	
\bigcirc	Drying at 68°F / 20°C	30-50 min Do not bake.	
	Sanding manual, wet	P320 - P500)
ë	Sanding manual, dry	P320 - P500	
S,	Orbital sanding, dry	P400 - P500	

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document

Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.