

# 285-270

DTM Urethane Primer Filler Pro - Grey - as a wet-on-wet sealer



A brand of BASF –  
We create chemistry

- Application:** Primer sealer for wet-on-wet application.
- Key Features:** Suitable for well-cured old paint, steel, aluminum and galvanized metal and GRP/SMC. Excellent corrosion protection.
- Remarks:**
- Clean substrate with Glasurit 700-10 before applying 285-270.
  - Remove all corrosion and rust beforehand by sanding or blasting.
  - No need to sand new e-coated parts.
  - Minimum temperature for air drying: 60°F (15°C).

---

**VOC ready for use**                      540 g/l                      4.5 lb/gal

---

**4:1:1**



**Mixing Ratio**

100 parts by volume                      285-270



**Hardener**

25 parts by volume                      929-58



**Reducer**

25 parts by volume                      352-50, -91, -216



**Spray viscosity at 68°F / 20°C**

DIN 4:                      15-20 s

**Potlife at 68°F / 20°C**

90 min

---

**Safety advice:**



Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.

# 285-270

DTM Urethane Primer Filler Pro - Grey - as a wet-on-wet sealer



A brand of BASF –  
We create chemistry

Application:	 Compliant gravity-feed spray gun	 HVLP spray gun
Nozzle pressure		10 psi
Nozzle size		1.3-1.4 mm
Number of spraycoats	1/2 + 1 (1/2 over body filler; 1 full coat over whole area)	
Flash-off at 68°F / 20°C	5 min between coats	
Film thickness	1.2-1.4 mil (30 - 40 micron)	



**Drying at 68°F / 20°C**      25-30 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document

### Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.