

285-38

HS Non-Sanding Sealer - White







A brand of BASF –
We create chemistry

- Application:** Wet-on-wet sealer for economical repairs.
- Key Features:** To get different grey colors, mix 285-38 with 285-49 Glasurit Non-Sanding Sealer black. Color formulations are available.
- Remarks:**
- Before filler application, fine sand body-filled areas and old paintwork with 280 - 320 (dry). Use Guide Coat.
 - Glasurit 285-38 will provide adequate adhesion and corrosion protection over steel and aluminum. For areas larger than 1 inch x 1 inch, Glasurit 285-38 should be applied over Glasurit 283-155 Etching Primer or Glasurit 801- Epoxy Primers.
 - 285-38 can be tinted with 568-408. Please see specific TDS for details.

VOC ready for use 540 g/l 4.5 lb/gal

2:1+30 %

	Mixing Ratio	100 parts by volume	285-38
	Hardener	50 parts by volume	929-51, -53
	Reducer	30 parts by volume	352-91, -216
	Spray viscosity at 68°F / 20°C	DIN 4:	16-18 s
	Potlife at 68°F / 20°C	2 h	

Safety advice:



Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.

285-38

HS Non-Sanding Sealer - White



A brand of BASF –
We create chemistry

Application:	 Compliant gravity-feed spray gun	 HVLP spray gun
Nozzle pressure		10 psi
Nozzle size		1.3-1.4 mm
Number of spraycoats	2 (one on body-filled area and one on entire surface to be painted)	
Flash-off at 68°F / 20°C	10-20 min (10 min - solids. 15-20 min - topcoat / basecoat metallics (matte).)	
Film thickness	0.8-1.4 mil	

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document

Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.