

285-50

HS Primer Filler - Grey - Flexible with 522-111 (2:1 Pre-Mix)



A brand of BASF –
We create chemistry

- Application:** A flexed high solids primer surfacer with outstanding dry sanding characteristics.
- Key Features:** Fast drying even at low temperatures. High build, easy to apply. Good corrosion and weather resistance. Excellent topcoat holdout.
- Remarks:**
- Choose hardeners and reducers according to temperature and size of object to be painted.
 - Use a guide coat to obtain better sanding results.
 - Can be applied as a high build filler in 3-4 coats (6.0 mils max), however dry times will be lengthened.

VOC ready for use 575 g/l 4.8 lb/gal



Mixing Ratio Pre-Mix

100 parts by volume 285-50
50 parts by volume 522-111

4:1:1



Mixing Ratio

100 parts by volume Pre-Mix



Hardener

25 parts by volume 929-51, -53



Reducer

25 parts by volume 352-50, -91, -216



Spray viscosity at 68°F / 20°C

DIN 4: 16-20 s

Potlife at 68°F / 20°C

1 h

Safety advice:



Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.






285-50

HS Primer Filler - Grey - Flexible with 522-111 (2:1 Pre-Mix)



A brand of BASF –
We create chemistry

Application:	 Compliant gravity-feed spray gun	 HVLP spray gun
Nozzle pressure		10 psi
Nozzle size		1.5-1.8 mm
Number of spraycoats	2-3	
Flash-off at 68°F / 20°C	5 min between coats	
Film thickness	2-2.5 mil (6 mils max)	

	Drying	929-51	929-53
	Drying at 68°F / 20°C	2.5 h	3.5 h
	Drying at 140°F / 60°C	25 min	
	Infrared (short wave)	8 min	
	Infrared (medium wave)	10-15 min	

	Sanding manual, wet	P400-P600
	Sanding manual, dry	P360-P400
	Orbital sanding, dry	P400-500

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document

Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.