

522-20

Universal Rapid Additive



A brand of BASF –
We create chemistry

- Application:** Drying accelerator for clearcoats for blending. Drying accelerator for Glasurit HS Urethane Topcoat 22-Line.
- Key Features:** Fast through dry, dust free and polishability. Used at low temperatures (60°-65°F/15°-18°C) or when fast curing, polishing and masking tape resistance is required. Used with signwriting and multi-color finishes.
- Remarks:**
- Measure amount of 522-20 carefully!
 - In 923-Clearcoats, use 2% max. Add up to 0.65 oz / 17 gms per quart of ready-to-spray material. For additional information, refer to the relevant clearcoat TDS.
 - In 22-Line, use 4% max. Add up to 1.25 oz / 33 gms per quart of ready-to-spray material. For more information, refer to the relevant 22-Line TDS.
 - Can be added to 285-270 with no adverse effects to the primers functionality. See relevant TDS for details.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document

Safety advice:

VOC as packaged: 497 g/L (4.2 lbs/gal)

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.