

522-333

Low VOC Elastifier Additive



A brand of BASF –
We create chemistry

Application:

Plasticizing additive for plastics painting.

Remarks:

- Use only 285- series when using 522-333 in undercoats. However, 522-333 **can not** be used in 285-81.
- For rigid plastics, no 522-333 is required.
- For soft plastics and foams, use 25% - 50% of 522-333. See relevant undercoat / clearcoat / topcoat TDS for more details.
- No 522-333 required in undercoats for painting of fiberglass reinforced plastics.
- Allow approximately 50% more dry time when using 50% 522-333. See relevant undercoat / clearcoat / topcoat TDS for details.
- All bumpers to be considered flexible.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document

Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.