

# 55-B500

Blending Clear



A brand of BASF –  
We create chemistry

- Application:** Blending Clear 55-B500 is used for blending in 55-Line metallic basecoats. This Blending Clear helps to achieve a smooth homogeneous overspray area in the fade-out zone, avoiding dark shadows around the repair area.
- Key Features:** May be used as an orientation coat (uniform finish blender) before application of metallic basecoat.
- Remarks:** The same spray gun can be used for Glasurit 55-B500 Blending Clear and 55-Line basecoat without having to be cleaned in between.

**VOC ready for use**                      825 g/l              6.9 lb/gal



**Mixing Ratio**

Ready for use.  
Mix well before using.



**Spray viscosity at 68°F / 20°C**

DIN 4:              17-19 s

**Application:**



**Compliant gravity-feed spray gun**



**HVLP spray gun**

**Nozzle pressure**

10 psi

**Nozzle size**

1.2-1.3 mm

**Number of spraycoats**

1  
wet coat

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document

**Safety advice:**

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.