

801-72

Epoxy Primer Filler - Grey - as a wet-on-wet sealer - Tinted with 568-408



A brand of BASF –
We create chemistry

Application:	Wet-on-wet sealer, tinted with 568-408
Key Features:	Good corrosion protection on bare steel, galvanized steel and aluminum.
Remarks:	<ul style="list-style-type: none"> • Chromate-free • Minimum temperature for air drying: +60°F / 15°C.

VOC ready for use	540 g/l	4.5 lb/gal
--------------------------	---------	------------

	Mixing Ratio Pre-Mix	100 parts by volume	801-72
		10 parts by volume	568-408

4:1:1

	Mixing Ratio	100 parts by volume	Pre-Mix
	Hardener	25 parts by volume	965-60
	Reducer	25 parts by volume	352-91, -216
	Spray viscosity at 68°F / 20°C	DIN 4:	18-20 s
	Potlife at 68°F / 20°C	8 h	

Safety advice:



Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.

801-72

Epoxy Primer Filler - Grey - as a wet-on-wet sealer - Tinted with 568-408



A brand of BASF –
We create chemistry

Application:	 Compliant gravity-feed spray gun	 HVLP spray gun
Nozzle pressure		10 psi
Nozzle size		1.3-1.4 mm
Number of spraycoats	1/2 + 1	
Flash-off at 68°F / 20°C	20 min	
Film thickness	1-1.4 mil	

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document

Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.