923-220



Low VOC Multi-Purpose Gloss Clear - Gloss Reducing with 522-422

Application: 2 component clear for topcoating Glasurit basecoat colors, with gloss reducing additive for matte

finish

Key Features: Excellent resistance to weathering and yellowing. Excellent flow, leveling and sag resistance. High

gloss.

Remarks:• Choose hardener and reducer according to temperature and size of object to be painted. Drying time

will vary accordingly.

· Using 522-422 will reduce the usable potlife of 923-220

VOC ready for use 250 g/l 2.1 lb/gal

100 parts by volume 923-220 Mixing Ratio Pre-Mix

50 parts by volume 929-100, -105, -115, -120, -130

Mixing Ratio 100 parts by volume Pre-Mix

Reducer 0-10 parts by volume 352-25, -45

Optional - no reducer is required

Additive 0-100 parts by volume 522-422

Spray viscosity at 68°F / DIN 4: 14-16 s

Potlife at 68°F / 20°C 3 h

Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.

923-220

Drying at 140°F / 60°C

30 min



Low VOC Multi-Purpose Gloss Clear - Gloss Reducing with 522-422

Application:	Compliant gravity-feed spray	HVLP spray gun
Application pressure	20-29 psi	
Nozzle pressure		10 psi
Nozzle size		1.2-1.4 mm
Number of spraycoats	2 medium wet coats	
Flash-off at 68°F / 20°C	5 min between coats	
Film thickness	2-2.5 mil	
Drying at 68°F / 20°C	² h	

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document

Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.