A brand of BASF – We create chemistry

923-222

Fast Repair Low VOC Clear - Flexible with 522-333

Application:		Flexible 2 component clear for topcoating catalyzed 55-Line and 90-Line basecoat.		
Key Features:		Excellent resistance to weathering and yellowing. Excellent flow, leveling and sag resistance. High gloss.		
Remarks:		 When using 923-222 over 55-Line, the use of 355-55 in the basecoat is required (10:1:4). Choose hardener and reducer according to temperature and size of object to be painted. Drying time will vary accordingly. To polish or remove dust particles: after 24 hrs. air dry, or when cool after force drying, wet sand with 1500 grit or finer sandpaper and then polish with fine polishing compound and/or liquid polish. Two mils of clearcoat (dry film) must remain over basecoat. If extensive color sanding is anticipated, apply an additional coat of clear. 		
VOC ready for use		250 g/l 2.1 lb/gal		
	Mixing Ratio Pre-Mix	4 parts by volume923-2221 parts by volume522-333		
		2:1+10 %		
	Mixing Ratio	100 parts by volume Pre-Mix		
Â	Hardener	50 parts by volume 929-100, -105, -115, -120, -130		
£	Reducer	10 parts by volume 352-25, -45		
S	Spray viscosity at 68°F / 20°C	DIN 4: 14-17 s		
	Potlife at 68°F / 20°C	1 h		

Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.

923-222

Fast Repair Low VOC Clear - Flexible with 522-333

Application:		Compliant gravity-feed spray	HVLP spray gun
Application pressure		20-29 psi	
Nozzle pressure			10 psi
Nozzle size			1.2-1.4 mm
Number of spraycoats		2-3	
Flash-off at 68°F / 20°C		2-5 min between coa	ts
Film thickness		2-2.5 mil	
\bigcirc	Drying at 68°F / 20°C Drying at 140°F / 60°C	2 h 15 min	
R	Infrared (short wave)	6-7 min	

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document

Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.