923-230



Low VOC Multi-Purpose Gloss Clear - 3:1 Mixing ratio

Application:

Key Features:

Remarks:

2 component clear for topcoating Glasurit basecoat colors.

Fast Drying. Excellent hold-out under all environmental conditions.

- Choose hardener according to temperature and size of object to be painted. Drying time will vary accordingly.
- 352-720 is recommended for use in normal to high temps and normal to lower humidities.
- 352-740 is recommended for use in normal to high temps and normal to high humidities.
- To polish or remove dust particles: after 24 hrs. air dry, or when cool after force drying, wet sand with 1200 grit or finer sandpaper and then polish with fine polishing compound and/or liquid polish. Two mils of clearcoat (dry film) must remain over basecoat. If extensive color sanding is anticipated, apply an additional coat of clear.
- 923-230 can be mixed using one of two possible mix ratios (2:1 or 3:1) as needed depending on your shop or weather conditions and the type of repair.
- 923-230 can be used with the following additives: 522-333 for flexible parts, and 522-20 for speed cure. Please see the relevant TDSs for more information.

VOC ready	for use	250 g/l	2.1 lb/gal	
		3:1+20 %		
	Mixing Ratio	300 parts by	volume	923-230
	Hardener	100 parts by	volume	929-245, -250
	Reducer	60 parts by volume		352-720, -740
s	Spray viscosity at 68°F / 20°C	DIN 4:	14-16 s	
	Potlife at 68°F / 20°C	1 h		

Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.

923-230

Drying at 68°F / 20°C

Drying at 140°F / 60°C



Low VOC Multi-Purpose Gloss Clear - 3:1 Mixing ratio

2-4 h

30 min

Application pressure 20-2 Nozzle pressure Nozzle size	9 psi 10 psi
	10 psi
Nozzle size	
	1.2-1.4 mm
Number of spraycoats	2 medium wet coats
Flash-off at 68°F / 20°C	5 min between coats
Film thickness	2-2.5 mil

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document

Safety advice:

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Safety Data Sheet (SDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.