22-AT 9050





Eco Balance 22 Line black

Application: AraClass - Eco Balance 22 Line ready mixed color.

Key Features: Eco effectiveness topcoat - black.

Remarks: Select AraClass hardener and AraClass reducer according to ambient temperature and size of object to

be painted.

3:1:1

Mixing Ratio 100 % by volume 22-AT 9050

Hardener 33 % by volume A-H-410, -H-430, -H-440 Eco Balance top coat hardener

Reducer 33 % by volume A-R-110, -R-120, -R-130

Eco Balance reducer

Spray viscosity at 20°C DIN 4: 18-22 s Potlife at 20°C 2 h

Application:		Compliant gravity-feed spray gun	HVLP spray gun
Application pressure	bar	2	2
Nozzle pressure	bar		0.7
Nozzle size		1.3-1.4	1.3
Number of spray coats		2	
Flash off at 20°C	min	approx. 5 minutes after each spray coat	
Film thickness	μm	50-70	
Application Remark		Alternatively: 1 ½ spray coats (no flash-off between coats required).	

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 $\mu m.$

2004/42/IIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

22-AT 9050

ECO BALANCE
Repair and protect.



Eco Balance 22 Line black



Drying at 20°C

8 h

Drying at 60°C

30 min



Infrared (short wave)

8 min

Drying Remark

Drying times can be influenced by the selection of hardener, reducer and application.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 $\mu m.$

2004/42/IIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.