

A-C-24

Variant with A-A-14 Eco Balance flex additive



A brand of BASF –
We create chemistry

Application: A-C-24 Eco Balance clear coat, ultimate drying with A-A-14 Eco Balance flex additive.
Key Features: Elastified
Remarks: Addition of 25% by vol.



Mixing Ratio PreMix

4	A-C-24
1	A-A-14

3:1:1



Mixing Ratio 100 % by volume PreMix



Hardener 33 % by volume A-H-430
Eco Balance topcoat hardener



Reducer 33 % by volume A-R-110, -R-120, -R-130
Eco Balance reducer



Spray viscosity at 20°C DIN 4: 17-19 s

Potlife at 20°C 30 min

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.




The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

A-C-24

Variant with A-A-14 Eco Balance flex additive



A brand of BASF –
We create chemistry

Application:	 Compliant gravity-feed spray gun	 HVLP spray gun
Application pressure	2 bar	
Nozzle size	1.2-1.3	
Number of spray coats	2	
Flash off at 20°C	1 - 3 min intermediate flash off between the spray coats. No flash off before oven drying.	
Film thickness	40-50 µm	
	Drying at 20°C	16 h
	Drying at 40°C	35 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/II B(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.