

A-C-30

Variant with A-A-40 Eco Balance texture additive



A brand of BASF –
We create chemistry

Application: A-C-30 Eco Balance clear coat, superior gloss with A-A-40 Eco Balance texture additive.
Remarks: Add up to 50% of A-A-40 to produce the desired texture or mix as per published mixing formula.



Mixing Ratio PreMix

2 A-C-30
1 A-A-40

Or quantities as per published formula.

3:1:1



Mixing Ratio

100 % by volume PreMix



Hardener

33 % by volume A-H-430
Eco Balance topcoat hardener



Reducer

33 % by volume A-R-120
Eco Balance reducer



Spray viscosity at 20°C

DIN 4: 18-21 s

Potlife at 20°C

6 h

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.



The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

A-C-30

Variant with A-A-40 Eco Balance texture additive



A brand of BASF –
We create chemistry

| Application: |  Compliant gravity-feed spray gun |  HVLP spray gun |
|-----------------------|--|--|
| Application pressure | 2 bar | |
| Nozzle pressure | | 0.7 bar |
| Nozzle size | 1.3-1.4 | 1.3 |
| Number of spray coats | 2 | |
| Flash off at 20°C | Flash off until mat between spray coats and before stoving. | |
| Film thickness | 50-70 µm | |



Drying at 20°C 10 h

Drying at 60°C 30 min



Infrared (short wave) 8 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.