

# A-P-50

Activation wipes



A brand of BASF –  
We create chemistry

<b>Application:</b>	AraClass - undercoat solutions.
<b>Key Features:</b>	Eco effectiveness wipes - highest surface quality. Wipes increase the corrosion resistance and the adhesion of the paint system, due to their chemical reaction with metal surfaces.
<b>Remarks:</b>	Recoatable with all AraClass undercoat materials, except polyester body filler or waterborne filler. Do not overcoat directly with basecoat or topcoat.

## Handling



**Cleaning**  
with A-P-25 / A-P-30

### Product suitable on cleaned bare metal such as



- Steel
- Galvanised sheet steel
- Aluminium

### Application



Evenly wet the entire bare metal surface with wipes. Wipe with overlapping single cross coats. The surface must stay moist for at least 1 minute. This is imperative for the chemical reaction to complete and form a passivation layer.

Spreading rate: per cloth max. 3 m<sup>2</sup>.

Flash off at 20°C: mat surface (max. 8h).

Close the container immediately after removing a wipe to protect the other wipes from drying out.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

## Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

**2004/42/IIIB(c III)(780)8:** The EU limit value for this product (product category: IIB.c III) in ready-for-use form is max 780 g/litre of VOC. The VOC content of this product is 8 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.