

# A-U-39

Variant for wet-on-wet application (metal)



A brand of BASF –  
We create chemistry

<b>Application:</b>	AraClass - Eco Balance undercoat solutions.
<b>Key Features:</b>	Eco Balance DTM, black. No need to sand new e-coated parts.
<b>Remarks:</b>	A-U-39 can be mixed with A-U-33 to achieve different grey shades. Clean the surface with A-P-25 Eco Balance universal waterborne cleaner before applying A-U-39.

## Handling

### Product is suitable on



- Sheet steel
- Galvanised sheet steel
- Aluminium
- OEM parts with e-coat
- Old paintwork

		<b>4:1:1</b>	
	<b>Mixing Ratio</b>	100 % by volume	A-U-39
	<b>Hardener</b>	25 % by volume	A-H-600
	<b>Reducer</b>	25 % by volume	A-R-125, -R-110, -R-120, -R-130
	<b>Spray viscosity at 20°C</b>	DIN 4: 15-20 s	
	<b>Potlife at 20°C</b>	90 min	

## Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

**2004/42/IIIB(c I)(540)539:** The EU limit value for this product ( product category: IIB.c I ) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.



The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

# A-U-39

Variant for wet-on-wet application (metal)



A brand of BASF –  
We create chemistry

Application:	 Compliant gravity-feed spray gun	 HVLP spray gun
Application pressure	2 bar	
Nozzle pressure		0.7 bar
Nozzle size	1.3-1.4	1.3
Number of spray coats	½ + 1	
Flash off at 20°C	Flash off between spray coats until mat and 25 - 30 min flash off after application.	
Film thickness	30-40 µm	
Application Remark	(half spray coat on body filler area and one spray coat whole repair area)	

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



### Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

**2004/42/IIIB(c I)(540)539:** The EU limit value for this product ( product category: IIB.c I ) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.