

A-U-86

Eco Balance UV primer filler, light grey



A brand of BASF –
We create chemistry

Application:	AraClass - Eco Balance undercoat solutions.
Key Features:	Eco effectiveness - UV primer filler. For good corrosion resistance, excellent topcoat holdout.
Remarks:	Clean with A-P-15 or A-P-25.

Handling

Product is suitable on

- Sheet steel
- Galvanised sheet steel
- Aluminium
- Old paintwork
- GRP / SMC



Shake vigorously for 2 min before each use.



Do not expose to sunlight in storage.
Do not apply in direct sunlight.

Material is ready for use.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(c 1)(540)540: The EU limit value for this product (product category: IIB.C I) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 540 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

A-U-86

Eco Balance UV primer filler, light grey



A brand of BASF –
We create chemistry

Application:	Compliant gravity-feed spray gun	HVLP spray gun
Application pressure	bar	2
Nozzle pressure	bar	0.7
Nozzle size		1.1-1.2
Number of spray coats		½ + 1
Flash off at 20°C	min	20 s between the first and the second coat.
Film thickness	µm	max. 80 µm
Application Remark	Alternatively: max.120 µm with 60s between the first and the second coat and 90s flash off before UV drying.	



UV Curing

5 min (UV-A > 6 mW/ cm²)

By using LED lamps, the drying time can be reduced due to their higher intensity in the decisive wavelength range. This must be checked individually.



Orbital sanding, dry

P400-P600

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(c 1)(540)540: The EU limit value for this product (product category: IIB.C I) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 540 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.