

P-U-32

Filler, tintable



A brand of BASF –
We create chemistry

Application: ProClass - undercoat solutions.

Key Features: Efficient filler - adhesion promoter. Efficient filler - sanding or wet-on-wet tintable filler. For tinting with Line 22 bases as colored filler.

Remarks: Use with colours that have poor hiding power, Never use 22 Line mixing bases on their own, be sure to mix them with mixing clear P-T-20 first!

Handling

Product is suitable on

- OEM parts with e-coat
- Old paintwork
- GRP / SMC



If bare metal areas are primed, the product can be used on

- Sheet steel
- Galvanised sheet steel
- Aluminium



Mixing Ratio PreMix:

- 100 % by volume P-U-32
- 50 % by volume 22 Line (Mixing formula with P-T-20)

4:1:1



Mixing Ratio

100 % by volume PreMix



Hardener

25 % by volume P-H-230



Reducer

25 % by volume P-R-110, -R-120, -R-130



Spray viscosity at 20°C

DIN 4: 18-20 s Potlife at 20°C 60 min

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(c I)(540)530: The EU limit value for this product (product category: IIB.c I) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 530 g/litres.



The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

P-U-32

Filler, tintable



A brand of BASF –
We create chemistry

Application:	 Compliant gravity-feed spray gun	 HVLP spray gun
Application pressure	bar	2
Nozzle pressure	bar	0.7
Nozzle size		1.6-1.8
Number of spray coats		2
Film thickness	µm	40-60



Drying at 20°C 4 h
Drying at 60°C 40 min



Infrared (short wave) 8 min



Orbital sanding, dry

P400-P500 (only after drying at 60°C or drying over night)

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(c I)(540)530: The EU limit value for this product (product category: IIB.c I) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 530 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.