

P-U-43

Variant Sanding Filler with P-A-914 for paintable plastics



A brand of BASF –
We create chemistry

- Application:** ProClass - undercoat solutions.
- Key Features:** Additive P-A-914 Plastic adhesion additive which makes P-U-43 suitable for direct application to all paintable plastic substrates.
- Remarks:** P-U-43 can be mixed with P-U-49 to achieve different grey shades.

Handling



Use on plastic substrates in combination with P-A-914 Plastic adhesion additive.

Product is suitable on

Pur-RIM / PP-EPDM / ABS / GRP-SMC / PC-PBTP / PA / PPO / rigid PVC

3:1:1



Mixing Ratio

100 % by volume P-U-43



Hardener

33 % by volume P-H-230



Reducer

33 % by volume P-A-914



Spray viscosity at 20°C

DIN 4: 17-19 s **Potlife at 20°C** 60 min

Application:



Compliant gravity-feed spray gun



HVLP spray gun

Application pressure bar

2

Nozzle pressure bar

0.7

Nozzle size

1.3-1.4

1.3-1.4

Number of spray coats

2

Film thickness

µm

40-60

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/II B(c I)(540)539: The EU limit value for this product (product category: IIB.c I) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

P-U-43

Variant Sanding Filler with P-A-914 for paintable plastics



A brand of BASF –
We create chemistry



Drying at 60°C 25 min



Sanding manual, dry P500-P800



Orbital sanding, dry P400-P500

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(c I)(540)539: The EU limit value for this product (product category: II.B.c I) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.