P-U-77

DTM primer filler, grey



Application: ProClass - undercoat solutions.

Key Features: Efficient DTM - primer, primer filler and filler.

For direct use on metal substrates with special anti-corrosive properties.

Remarks: Clean the surface with P-P-26 before applying P-U-77.

Handling

Product is suitable on

· Sheet steel



- · Galvanised sheet steel
- · Aluminium
- · OEM parts with e-coat
- · Old paintwork

5:1:1



Mixing Ratio 100 % by volume P-U-77



Hardener 20 % by volume P-H-131



Reducer 20 % by volume P-R-110, -R-120, -R-130



Spray viscosity at 20°C DIN 4: 18-20 s Potlife at 20°C 90 min

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles $< 0.1 \mu m$.

2004/42/IIB(c I)(540)539: The EU limit value for this product (product category: IIB.c I)in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

P-U-77

DTM primer filler, grey



Application:		Compliant gravity-feed spray gun	HVLP spray gun	
Application pressure bar		ar	2	
Nozzle pressure bar		ar		0.7
Nozzle size			1.6-1.8	1.7-1.9
Number of spray coats			½ + 1	
Film thickness µm			50-70	
	Drying at 20°C	16 h		
()	Drying at 60°C	35 min		
R	Infrared (short wave)	9 min		
S E	Orbital sanding, dry		P	400-P500

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles $< 0.1 \mu m$.

2004/42/IIB(c I)(540)539: The EU limit value for this product (product category: IIB.c I)in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

always be observed in addition to the processing instructions given within this document.