

P-U-79

Variant high-build primer filler



A brand of BASF –
We create chemistry





Application:	ProClass - undercoat solutions.
Key Features:	DTM primer filler, black. No need to sand new e-coated parts.
Remarks:	P-U-79 can be mixed with P-U-73 to achieve different grey shades. Clean the surface with P-P-26 before applying P-U-79.

Handling

Product is suitable on



- Sheet steel
- Galvanised sheet steel
- Aluminium
- OEM parts with e-coat
- Old paintwork

		5:1:1		
	Mixing Ratio	100 % by volume	P-U-79	
	Hardener	20 % by volume	P-H-131	
	Reducer	20 % by volume	P-R-110, -R-120, -R-130	
	Spray viscosity at 20°C	DIN 4: 18-20 s	Potlife at 20°C	90 min

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(c I)(540)539: The EU limit value for this product (product category: IIB.c I) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.







The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

P-U-79

Variant high-build primer filler



A brand of BASF –
We create chemistry

Application:	 Compliant gravity-feed spray gun	 HVLP spray gun
Application pressure	bar 2	
Nozzle pressure	bar	0.7
Nozzle size	1.6-1.8	1.7-1.9
Number of spray coats		½ + 2
Film thickness	µm 80-120	
 Drying at 20°C	16 h	
 Drying at 60°C	45 min	
 Infrared (short wave)	15 min	
 Orbital sanding, dry		P400-P500

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(c I)(540)539: The EU limit value for this product (product category: IIB.c I) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.