

P-U-30

Transparent adhesion promoter



A brand of BASF –
We create chemistry

Application: ProClass - undercoat solutions.





Key Features: Efficient filler - adhesion promoter.
No sanding before topcoat or basecoat application; safe application; no overspray visible in door shuts as filler is transparent.

Handling



Product is suitable on

- OEM parts with e-coat
- Old paintwork
- GRP / SMC

		3:1:1		
	Mixing Ratio	100 % by volume	P-U-30	
	Hardener	33 % by volume	P-H-230	
	Reducer	33 % by volume	P-R-110, -R-120, -R-130	
	Spray viscosity at 20°C	DIN 4: 15-19 s	Potlife at 20°C	3 h

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(c I)(540)525: The EU limit value for this product (product category: IIB.c I) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 525 g/litres.



The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

P-U-30

Transparent adhesion promoter



A brand of BASF –
We create chemistry

Application:	 Compliant gravity-feed spray gun	 HVLP spray gun
Application pressure	bar	2
Nozzle pressure	bar	0.7
Nozzle size		1.3-1.4
Number of spray coats		1-2
Film thickness	µm	20-30



Drying at 20°C 20-30 min

Remark

Apply topcoat wet-on-wet.
Intermediate sanding is required when flash off time exceeds 3 hours at 20°C.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/II B(c I)(540)525: The EU limit value for this product (product category: IIB.c I) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 525 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.