































Pre-treatment of substrates and old paintwork

Metallic Substrates

| | | | | | | | |
|-------------------------|-------------------------------------|---|--|--|-------------------------------------|---|--|
| Sheet steel | 360-4 Glasurit® Metal cleaner |  1 x |  wipe dry |  P80-P150 | 360-4 Glasurit® Metal cleaner |  1 x |  wipe dry |
| Galvanised steel | 360-4 Glasurit® Metal cleaner |  1 x |  wipe dry |  sanding pad | 360-4 Glasurit® Metal cleaner |  1 x |  wipe dry |
| Aluminium | 360-4 Glasurit® Metal cleaner |  1 x |  wipe dry |  P150- P180 | 360-4 Glasurit® Metal cleaner |  1 x |  wipe dry |

Plastics

| | | | | | | | | |
|--|---|---|--|--|---|---|--|--|
| Plastics | 541-30 Glasurit® Universal cleaner for plastics |  1 x |  wipe dry |  damaged area: P80-P600 entire part: sanding pad | 541-30 Glasurit® Universal cleaner for plastics |  1 x |  wipe dry | |
| Plastics PU foam and polyamide (PA) | Heating to remove mould release agents and water |  60 °C 1 hour | 541-30 Glasurit® Universal cleaner for plastics |  1x moistened cloth |  damaged area: P80-P600 entire part: sanding pad | 541-30 Glasurit® Universal cleaner for plastics |  1 x |  wipe dry |
| GRP/SMC | 541-30 Glasurit® Universal cleaner for plastics |  1 x |  wipe dry |  P180- P240 | 541-30 Glasurit® Universal cleaner for plastics |  1 x |  wipe dry | |

Safety advice:

















The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

Pre-treatment of substrates and old paintwork

Old paintwork / new panels

| | | | | | | | |
|--|--|---|--|--|---|---|--|
| New panels factory- primed | 541-5 Glasurit® Wax and Silicone Remover |  1 x |  wipe dry |  sanding pad or P240- P320 | 541-5 Glasurit® Wax and Silicone Remover |  1 x |  wipe dry |
| | | | | | | | |
| Old paintwork | 541-5 Glasurit® Wax and Silicone Remover |  1 x |  wipe dry |  sanding pad or P240- P320 | 541-5 Glasurit® Wax and Silicone Remover |  1 x |  wipe dry |
| | | | | | | | |
| Old paintwork solvent- sensitive | 700-10 Glasurit® Degreasing and cleansing agent |  1 x |  wipe dry |  sanding pad or P240- P320 | 700-1 Glasurit® Cleaner |  1 x |  wipe dry |
| | | | |  P320- P400 fade- out area | | | |

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.