


































Glasurit® RATIO Classic

Properties:

Solvent-borne repair process for a fast, economical quality finish

Cleaning	541-5 Glasurit® Wax and Silicone Remover	 1 x	 wipe dry	Mechanical de-rusting of damaged areas	 P16-P150	541-5 Glasurit® Wax and Silicone Remover	 1 x	 wipe dry														
	Body Filler (coarse + fine)	839-20 / 20K Glasurit® Multi Purpose Body Filler	948-36 Glasurit® Hardener Paste		 + 2-3%	 20-30 min. at 20°C	 4 min.	 P80/P150 coarse sanding	581-90 Glasurit® Guide Coat black	 P240/ P320 fine sanding	 541-5 1x	 wipe dry										
Primer		283-150 Glasurit® Etch Primer Filler	352-230 Glasurit® Activator	 1:1 mixing stick	 HVLP 1.3-1.7 mm 2.0-3.0 bar	 1 thin coat 10-15 µm	 10-15 min. at 20°C	Primer Filler	285-505, -555, -655 Glasurit® HS Primer Filler	929-55, -56 Glasurit® HS Primer Hardener	352- Glasurit® Reducer	 4:1:1 mixing stick	 HVLP 1.7-1.9 mm 2.0-3.0 bar	 2 50-70 µm	 20 min. at 60°C	 P400 - P500	 700-1 1x	 wipe dry				
	Topcoat	22 Line Glasurit® HS 2K Topcoat	929- Glasurit® HS Topcoat Hardener	352- Glasurit® Reducer	 2:1+10% mixing stick	 HVLP 1.3 mm 2.0-3.0 bar	 2 50-70 µm		 30 min. at 60 °C	Basecoat	55 Line Glasurit® Basecoat	352- Glasurit® Reducer	 2:1 mixing stick	 HVLP 1.3 mm 2.0-3.0 bar	 2 + 1/2 spraycoats	 approx. 10 min.	Clear	923-255 Glasurit® HS Multi Clear	929- Glasurit® HS Topcoat Hardener	352- Glasurit® Reducer	 2:1+10% mixing stick	 HVLP 1.3 mm 2.0-3.0 bar

or alternatively:

Glasurit® Primer Filler 285-700 /-730 /-790

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

