

22 Line Glasurit® HS 2K Topcoat VOC MC600



- Application:** Direct gloss HS solid-colour topcoat
- Properties:** High solids content; efficient; outstanding weathering resistance, yellowing resistance, hardness; very good curing; very good gloss and build
- Remarks:**
- Select reducers according to temperature and size of object.
 - Do not use mixing bases on their own, but always with 522-MC600 Mixing Clear (3:1)!**

	Paint system	S 10	
			Spreading rate: 475 m ² /l at 1 µm
	Mixing ratio	Weight in according to mixing formula. 3 : 1 : 1 100% by vol. 22 Line VOC MC600	
	Hardener	33% by vol. 929-61, -63, -64	
	Reducer	33% by vol 352-30 / -10 / -40	
	Spray viscosity DIN 4 at 20°C	approx. 18 - 22 s	Potlife at 20°C: 2 h
	Gravity cup Spraying pressure	HVLP-gravity-feed spray gun: 1.3 mm 2.0 – 3.0 bar 0.7 bar at the nozzle	Compliant gravity-feed spray gun: 1.3 -1.4 mm 2.0 bar
	Number of spraycoats	2	Film thickness: 50-70 µm
		½ + 1 can be applied to vertical surfaces (no flash-off between coats required)	Film thickness: approx. 50 µm
	Flash-off at 20°C	approx. 5 minutes after each spray coat	
	Drying at 20 °C	8 hours	
	Drying at 60 °C	30 min.	
	Infrared (short wave)	8 min.	
	Infrared (medium wave)	10 - 15 min.	

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

