











### 22 Line Glasurit® HS 2K Topcoat VOC

# G / T

- Application:** Direct gloss HS solid-colour topcoat
- Properties:** High solids content; efficient; outstanding weathering resistance, yellowing resistance, hardness; very good curing; very good gloss and build
- Remarks:**
- Select reducers according to temperature and size of object.
  - Do not use mixing bases on their own, but always with 522-MC35 Mixing Clear (4:1)!**

	<b>Paint system</b>	<b>S 10</b>	
			<b>Spreading rate:</b> 475 m <sup>2</sup> /l at 1 µm
	<b>Mixing ratio</b>	<b>Weight in according to mixing formula.</b> 2 : 1 + 10%, use mixing stick 100% by vol. 22 Line VOC	
	<b>Hardener</b>	50% by vol. 929-33, -31, -34	
	<b>Reducer</b>	10% by vol. 352-91 / -50 / -216 10% by vol 352-30 / -10 / -40	
	<b>Spray viscosity DIN 4 at 20°C</b>	approx. 20-24 s	<b>Potlife at 20°C:</b> 2-3 hours
	<b>Gravity cup Spraying pressure</b>	HVLP-gravity-feed spray gun: 1.3 mm 2.0 – 3.0 bar 0.7 bar at the nozzle	Compliant gravity-feed spray gun: 1.3 -1.4 mm 2.0 bar
	<b>Number of spraycoats</b>	2 ½ + 1 can be applied to vertical surfaces (no flash-off between coats required)	<b>Film thickness:</b> 50-70 µm <b>Film thickness:</b> approx. 50 µm
	<b>Flash-off at 20°C</b>	approx. 5 minutes after each spray coat	
	<b>Drying at 20 °C</b>	8 hours	
	<b>Drying at 60 °C</b>	30 min.	
	<b>Infrared (short wave)</b>	8 min.	
	<b>Infrared (medium wave)</b>	10 - 15 min.	

**Safety advice:**

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

**2004/42/IIIB(d)(420)419:** The EU limit value for this product ( product category: IIB.d ) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

