285-95



HS tintable Filler variant wet-on-wet for plastic with 522-10

Αp	pli	cati	on:

Transparent filler component suitable as a wet-on-wet surfacer.

3:1:1

for plastics

Mixing Ratio

100 % by volume

285-95



Hardener

33 % by volume

929-56, -55



Reducer

33 % by volume

522-10



Spray viscosity at 20°C

DIN 4:

18-20 s

Potlife at 20°C

1 h

Application:		Compliant gravity-feed spray gun	₩ HVLP spray gun	
Application pressure	bar	2	2-3	
Nozzle pressure	bar		0.7	
Nozzle size		1.3-1.4	1.3	
Number of spray coats		½ + 1 (body filled area / entire surface)		
Flash off at 20°C	min	15-20		
Film thickness	μm	20-35		

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 μm .

2004/42/IIB(c II)(540)525: The EU limit value for this product (product category: IIB.c II)in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 525 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

285-95



HS tintable Filler variant wet-on-wet for plastic with 522-10



Sanding manual, dry

P500 - P800



Orbital sanding, dry

P400 - P500

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 $\mu m.$

2004/42/IIB(c II)(540)525: The EU limit value for this product (product category: IIB.c II)in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 525 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.