

283-150

Wash primer, light beige



A brand of BASF –
We create chemistry

Application:	Primer / Primer filler
Key Features:	Very good anti-corrosive properties, easy and quick sanding
Remarks:	For steel, aluminium and galvanised steel. Do not recoat with polyester body filler! Not recoatable with water based products.

2:1+10 %



Mixing Ratio

100 % by volume 283-150



Hardener

50 % by volume 352-228



Reducer

10 % by volume 352-10, -30, -50, -91



Spray viscosity at 20°C

DIN 4: 16-17 s **Potlife at 20°C** 48 h

Application:



**Compliant gravity-feed
spray gun**



HVLP spray gun

Application pressure bar

2

2-3

Nozzle pressure bar

0.7

Nozzle size

1.3-1.8

1.3-1.8

Number of spray coats

4

Film thickness

µm

30-35

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(c III)(780)760: The EU limit value for this product (product category: IIB.c III) in ready to use form is max 780 g/litre of VOC. The VOC content of this product is 760 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

283-150

Wash primer, light beige



A brand of BASF –
We create chemistry



Drying at 20°C 60 min

Drying at 60°C 20 min



Infrared (short wave) 3 min

Infrared (medium wave) 5-10 min



Sanding manual, dry

P800

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(c III)(780)760: The EU limit value for this product (product category: IIB.c III) in ready to use form is max 780 g/litre of VOC. The VOC content of this product is 760 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.