

151-130

UV primer filler, light grey



A brand of BASF –
We create chemistry

Application: Primer filler for metal
Key Features: Suitable for steel, galvanized steel and aluminium.
 Good corrosion resistance, excellent topcoat holdout.



Paint System

The material is ready for use.

Handling



Material should not be stirred.
 Shake vigorously for 2 min. before each use.



Do not apply in direct sunlight.
 Do not expose to sunlight in storage



Spray viscosity at 20°C DIN 4: 18-20 s **Potlife at 20°C**

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/II B(c II)(540)540: The EU limit value for this product (product category: IIB.C II) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 540 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

151-130

UV primer filler, light grey



A brand of BASF –
We create chemistry

Application:	Compliant gravity-feed spray gun	HVL P spray gun
Application pressure	bar	2
Nozzle pressure	bar	0.7
Nozzle size		1.1-1.2 / 1.2
Number of spray coats		½ + 1 151-130 appears transparent and should not be sprayed to cover
Flash off at 20°C	min	20 s between the first and the second coat.
Film thickness	µm	max. 80
Application Remark	Alternatively: Film thickness max. 120 µm with 60 s between the first and the second coat and 90 s flash-off before UV drying.	
UV Curing	5 min. (UV-A > 6 mW/ cm ²) By using LED lamps, the curing time can be reduced due to their higher intensity in the decisive wavelength range. This must be checked individually.	
Sanding manual, wet	P800	
Orbital sanding, dry	P400 - P500	

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIB(c II)(540)540: The EU limit value for this product (product category: IIB.C II) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 540 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.