

Glasurit® Primer Filler Pro, grey

G / PF

Application: Primer filler / primer / wet-on-wet filler

Properties: Suitable for steel, galvanized steel, aluminium, old paintwork and GRP / SMC
Good corrosion protection and weathering resistance, good finish quality
Anti-corrosion and adhesion primer for above mentioned substrates in Glasurit paint systems
Can be applied under 285- Glasurit primer fillers and primers

Remarks:

- Use 581-90 Glasurit Guide Coat, black as guide coat (for a better sanding result).
- No need to sand new e-coated parts.
- Parts coated with 285-270 can be overcoated without intermediate sanding for up to 5 days
- **Clean the surface with 700-10 Glasurit Degreasing and cleaning agent before applying 285-270.**
- Minimum temperature for air drying: +15°C.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.











2004/42/II B(c I)(540)539: The EU limit value for this product (product category: IIB.c II)in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



Glasurit® Primer Filler Pro, grey

G / PF

	Application	Primer Filler			
	Spreading rate	m ² / l at 1 µm			
	Mixing ratio	5 : 1 : 1 for metal 100% by vol. 285-270		5 : 1 : 1 for plastics 100% by vol. 285-270	
	Hardener	20% by vol. 929-58		20% by vol. 929-58	
	Reducer	20% by vol. 352-91, -50, -216 352-30, -10, -40		20% by vol. 522-10	
	Spray viscosity DIN 4 at 20°C	18 – 20 s			
	Potlife at 20 °C	90 min			
	Gravity cup Spraying pressure	HVLP spray gun: 1.7 – 1.9 mm 2.0 – 3.0 bar / 0.7 bar at the nozzle		Compliant gravity-feed spray gun 1.6 – 1.8 mm, 2.0 bar	
	Number of spraycoats	½ + 1			
	Film thickness	50 – 70 µm			
	Drying at 20 °C Drying at 60 °C	16 h for 35 min			
	Infrared (short wave)	9 min (4 min 60 °C, 5 min 80 °C)			
	Sanding: manual	P800			
	Sanding: orbital sander	P400 - P500			

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.








2004/42/II B(c I)(540)539: The EU limit value for this product (product category: IIB.c II)in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



Glasurit® Primer Filler Pro, grey

G / PF

	Application	Wet-on-Wet Filler for metal		Wet-on-Wet Filler for plastics		
	Spreading rate					m ² / l at 1 µm
	Mixing ratio	4 : 1 : 1 100% by vol.	285-270	4 : 1 : 1 100% by vol.	285-270	
	Hardener	25% by vol.	929-58	25% by vol.	929-58	
	Reducer	25% by vol.	352-91, -50, -216 352-30, -10, -40	25% by vol.	522-10	
	Spray viscosity DIN 4 at 20°C	15 – 20 s				
	Potlife at 20 °C	90 min				
	Gravity cup Spraying pressure	HVLP spray gun: 1.3 mm 2.0 – 3.0 bar / 0.7 bar at the nozzle		Compliant gravity-feed spray gun 1.3 – 1.4 mm, 2.0 bar		
	Number of spraycoats	½ + 1 = ½ x putty area / 1 x whole area		Film thickness: app. 30 - 40 µm		
	Flash-off at 20°C	25 - 30 min				

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.












2004/42/II B(c I)(540)539: The EU limit value for this product (product category: IIB.c II)in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



Glasurit® Primer Filler Pro, grey

G / PF

	Application	High-build primer filler	Primer
	Spreading rate	m ² /l at 1 µm	
	Mixing ratio	5 : 1 : 1 100% by vol. 285-270	
	Hardener	20% by vol. 929-58	
	Reducer	20% by vol. 352-91, -50, -216 352-30, -10, -40	
	Spray viscosity DIN 4 at 20°C	18 – 20 s	
	Potlife at 20 °C	90 min	
	Gravity cup Spraying pressure	HVLP spray gun: 1.7 – 1.9 mm 2.0 – 3.0 bar /0.7 bar at the nozzle Compliant gravity-feed spray gun 1.6 –1.8 mm 2.0 bar	HVLP spray gun: 1.3 – 1.7 mm 2.0 – 3.0 bar / 0.7 bar at the nozzle Compliant gravity-feed spray gun 1.3 – 1.7 mm 2.0 bar
	Number of spraycoats	½ + 2	1 thin coat (covering)
	Film thickness	80 – 120 µm	10 – 20 µm
	Flash-off at 20°C	-	10 – 15 min
	Drying at 20 °C Drying at 60 °C	16 h for 45 min	- -
	Infrared (short wave)	15 min (4 min 60 °C, 11 min 80 °C)	-
	Sanding: manual	P800	-
	Sanding: orbital sander	P400 - P500	-

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/II B(c I)(540)539: The EU limit value for this product (product category: IIB.c II)in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

