

285-555

HS Primer Filler, black variant with 522-55



A brand of BASF –
We create chemistry

- Application:** Efficient HS primer filler with excellent wet and dry sanding properties.
- Key Features:**
- Shorter drying time at room temperature.
 - Improved surface drying and curing.
- Remarks:** Use 522-55 Glasurit Air-Drying Primer Filler Additive only at room temperature >20°C. 522-55 will reduce the potlife.
Ambient temperature and film build can greatly affect the drying behaviour.

4:1:1



Mixing Ratio

100 % by volume 285-555



Hardener

25 % by volume 929-55



Reducer

25 % by volume 522-55



Spray viscosity at 20°C

DIN 4: 16-18 s **Potlife at 20°C** 30 min

Application:



Compliant gravity-feed spray gun



HVLP spray gun

Application pressure **bar**

2

2-3

Nozzle pressure **bar**

0.7

Nozzle size

1.6-1.8

1.7-1.9

Number of spray coats

2

Flash-off between spraycoats until mat, no flash-off before drying.

Film thickness **µm**

50-70

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(c I)(540)539: The EU limit value for this product (product category: IIB.c I) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

285-555

HS Primer Filler, black variant with 522-55



A brand of BASF –
We create chemistry



Drying at 20°C 40 min



Sanding manual, dry P800



Orbital sanding, dry P400 - P500

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(c I)(540)539: The EU limit value for this product (product category: IIB.c I) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.