801-72

EP Primer Filler grey



Application:

Key Features:

Remarks:

Primer filler/ wet-on-wet primer filler / adhesion promoter.

Good corrosion protection, high build, good finish, rub-resistant with 541-5 Wax and Silicone Remover.

- Can be tinted with max. 10% of 568-408 CV Primer Tinting Paste, black (mixture code: 801-72G).
- Minimum temperature for air drying: +15°C.
- · Best possible finish if 801-72 is force-dried.
- When being used as adhesion promoter, 801-72 can be filled with 839- knifing fillers after 3 hours at 20°C.



Spreading rate

425 m²/l at 1 μm

4:1:1



Mixing Ratio

100 % by volume

801-72



Hardener

25 % by volume

965-60



Reducer

25 % by volume

352-91, -30, -40, -216



Spray viscosity at 20°C

DIN 4:

18-20 s

Potlife at 20°C

8 h

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles $< 0.1 \mu m$.

2004/42/IIB(c II)(540)539: The EU limit value for this product (product category: IIB.c II) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

801-72

EP Primer Filler grey



Application:			Compliant gravity-feed spray gun		HVLP spray gun
Application pressure bar			2		2-3
Nozzle pressure bar					0.7
Nozzle size			1.6-1.8		1.7-1.9
Number of spray coats				2	
Film thickness µm				40-50	
	Drying at 20°C Drying at 60°C Infrared (short wave) Infrared (medium wave)	8 h 30 min 11 min 10-15 min			
E.	Sanding manual, wet			P800	

always be observed in addition to the processing instructions given within this document.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must

P400 - P500

Safety advice:

The products are suitable for professional use only.

Orbital sanding, dry

It cannot be ruled out that this product contains particles $< 0.1 \mu m$.

2004/42/IIB(c II)(540)539: The EU limit value for this product (product category: IIB.c II) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 539 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.