923-115

HS universal clear



Application: HS clear for Glasurit waterborne basecoat / clear coat systems.

Key Features: High solids content, safe to spray, excellent flow and levelling, fast drying, excellent surface hardness,

polishing behaviour and tape resistance.

Remarks: Select hardener and reducer according to ambient temperature and size of object to be painted.

Paint System

S 10

Spreading rate

330 m²/l at 1 μ m

2:1+10 %

Mixing Ratio 100 % by volume 923-115

Hardener 50 % by volume 929-31, -33, -34

Reducer 10 % by volume



Spray viscosity at 20°C DIN 4: 20-22 s Potlife at 20°C 2 h

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles $< 0.1 \mu m$.

2004/42/IIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

923-115

HS universal clear



Application:		Compliant gravity-feed spray gun	🕌 HVLP spray gun
Application pressure bar		2	
Nozzle pressure bar			0.7
Nozzle size		1.3-1.4	1.3
Number of spray coats		2	
Flash off at 20°C min		3 minutes between spraycoats	
Film thickness µm		40-60	
Application Remark		Alternatively: ½ + 1 spraycoats can be applied to vertical surfaces (no flash-off between coats required)	
	Drying at 20°C	10 h	
	Drying at 60°C	30 min	
R	Infrared (short wave)	8 min	
	Infrared (medium wave)	10-15 min	

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles $< 0.1 \mu m$.

2004/42/IIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.