










### Glasurit® MS-Racing Clear



- Application:** MS clear for basecoat/clearcoat systems. For use in quick repair on single panels or in spot repairs.
- Properties:** Fast curing, even when air dried at 20°C, very good polishing behaviour
- Remarks:**
- Select hardener, reducer and reducer percentage according to ambient temperature and size of object to be painted.

	<b>Paint system</b>		
	<b>VOC ready for use</b>	> 420 g/l	<b>Spreading rate:</b> 215 m <sup>2</sup> /l at 1 µm
	<b>Mixing ratio</b>	<b>2 : 1 + 10 - 30 %</b> 100% by vol. 923-144	
	<b>Hardener</b>	50% by vol. 929-91/-93	
	<b>Reducer</b>	10-30% by vol. 352-50/-91/-216 (depending on application)	
	<b>Spray viscosity DIN 4 at 20°C</b>	16 s	<b>Potlife at 20°C:</b> 4 h (929-93)
	<b>Gravity cup Spraying pressure</b>	HVLP-gravity-feed spray gun: 1.3 mm 2.0 – 3.0 bar 0.7 bar at the nozzle	Compliant gravity-feed spray gun: 1.3 -1.4 mm 2.0 bar
	<b>Number of spraycoats</b>	2 - 3	<b>Film thickness:</b> 50-60 µm
	<b>Drying at 20 °C</b>	<b>Tack-free</b> 929-91 = 1 hour 929-93 = 2 hours	<b>Polishable</b> 929-91 = 2 hours 929-93 = 4 hours
	<b>Drying at 60 °C</b>		929-91 = 15 min. 929-93 = 20 min.
	<b>Infrared (short wave) Infrared (medium wave)</b>	8 min. 10 - 15 min.	

**Safety advice:**

The products are suitable for professional use only.  
It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

