











### Glasurit® Air Dry Fast Clearcoat



- Application:** Only available in the region Asia / Pacific.  
2K fast clear for Glasurit basecoat / clearcoat systems. For a quick repair on 1 - 3 panels or in spot repairs.
- Properties:** Especially fast drying when air dried at 20°C. Very good polishing behaviour. Good quality finish.
- Remarks:** For spot repairs, ensure transition area of fade out zone has completely cured prior to polishing. IR drying is recommended.

	<b>Paint system</b>		
	<b>VOC ready for use</b>	> 420 g/l	
	<b>Mixing ratio</b>	<b>2 : 1</b> 100% by vol. 923-198	
	<b>Hardener</b>	50% by vol. 929-98	
	<b>Reducer</b>		
	<b>Spray viscosity DIN 4 at 20°C</b>	14 – 16 s	<b>Potlife at 20°C</b> 1.5 h
	<b>Gravity cup Spraying pressure</b>	HVLP gravity feed spray gun: 1.3 mm 2.0 – 3.0 bar / 0.7 bar at the nozzle	Compliant gravity feed spray gun: 1.3 – 1.4 mm 2.0 bar
	<b>Number of spraycoats</b>	2 medium coats	<b>Film thickness:</b> 40 - 60 µm
	<b>Flash-off at 20°C</b>	0 - 2 min. between spray coats	
	<b>Drying at 20 °C</b>	40 min.	
	<b>Polishable at 20°C 60°C</b>	40 min. after cooling	

**Safety advice:**

The products are suitable for professional use only.  
It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

