











Glasurit® MS-Clear extremely scratch-resistant



- Application:** MS clear for basecoat/clearcoat systems with an extreme resistance to scratches caused by car wash brushes, for example.
- Properties:** Fairly high solids content (medium solid), outstanding weathering and yellowing resistance, extremely scratch-resistant.
Especially suitable for the repair of original finishes with clears identified as scratch-resistant.
- Remarks:**
- Removal of dust nibs or runs only after very good curing.
 - Do not use any other hardener as otherwise the quality and scratch-resistance cannot be achieved.

	Paint system		
	VOC ready for use	> 420 g/l	Spreading rate: 250 m ² /l at 1 µm
	Mixing ratio	2 : 1 + 10% 100% by vol. 923-43	
	Hardener	50% by vol. 929-76	
	Reducer	10% by vol. 352-91/-216	
	Spray viscosity DIN 4 at 20°C	17 - 19 s	Potlife at 20°C: 2 hours
	Gravity cup Spraying pressure	HVLP-gravity-feed spray gun: 1.3 mm 2.0 – 3.0 bar 0.7 bar at the nozzle	Compliant gravity-feed spray gun: 1.3 -1.4 mm 2.0 bar
	Number of spraycoats	2	Film thickness: 50-60 µm
	Flash-off at 20°C	approx. 10 minutes <u>between</u> spraycoats	
	Drying at 20 °C	16 hours	
	Drying at 60 °C	45 min.	
	Infrared (short wave)	8 min.	
	Infrared (medium wave)	10 - 15 min.	

Safety advice:

The products are suitable for professional use only.
It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

