










## Glasurit® Stone chip and underbody protection



- Application:** Underbody and stone chip protection product or sealer
- Properties:**
- 1109-1240/6 ready for use, available in 1-litre cans, apply with Compliant gravity-feed spray gun
  - 1109-1240/4 and 1109-1503/3 paste-like apply with special gun or airless pumps
  - 1109- can be recoated
- Remarks:**
- Seal body-filled areas with Glasurit® 283- primer fillers.
  - Clean working tools with water immediately after use.
  - Remove overspray within 30 min. using a wet sponge or 352-91 Reducer.
  - 1109- can also be used as a sealer on bleeding old paintwork, peroxide patches and TPA substrates.
  - Underbody protection  
airless: nozzle 0.41-0.5 mm, pressure 120-180 bar (1800 – 2700 p.s.i.)  
pressure pot: 2-3 mm nozzle, atomisation pressure: 3-6 bar (45-90 p.s.i.);  
material pressure depends on desired texture

	Application	Underbody protection	Stone chip protection
	Paint system		
	Spreading rate	450 m <sup>2</sup> /l at 1 micron	466 m <sup>2</sup> /l at 1 micron
	Reducer	water, if required	max. 5% water, if required
	Spray viscosity DIN 4 at 20°C	ready for use	20 s
	Gravity cup Spraying pressure		HVLP gun: 1.9 mm 2.0-3.0 bar (30-45 p.s.i.) / 0.7 bar (10 p.s.i.) at the nozzle
	Number of spraycoats	4 - 6	1 - 2
	Film thickness	500-1.000 microns	40-50 microns
	Drying at 20 °C	6 hours	2 hours
	Drying at 60 °C	45 – 60 min.	30 min.
	Infrared (short wave)	8 min.	8 min.
	Infrared (medium wave)	10 - 15 min.	10 - 15 min.

### Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

**2004/42/IIIB(e)(840)46:** The EU limit value for this product ( product category: IIB.e ) in ready to use form is max 840 g/litre of VOC. The VOC content of this product is 46 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

