






Glasurit® Blend-in Reducer

G / X

Application:

- Blend-in reducer for 923- clears and 22 Line/22 Line VOC topcoats.
- Blend-in reducer to melt in overspray / overlap areas or to melt in clear coat/topcoat fade-out areas in blend-in repairs.

| | | | |
|--|--|---|---|
|  | Paint system | S 7, S 7a, S 8, S 9 | |
|  | Spray viscosity DIN 4 at 20°C | ready for use | |
|  | Gravity cup Spraying pressure | HVLP gun: 1.3 mm 2.0 – 3.0 bar / 0.7 bar at the nozzle | Compliant gravity-feed gun 1.3 – 1.4 mm, 2.0 bar |
|  | Number of spraycoats | 2 or 3 (clear coat / topcoat fade-out areas) | |
|  | Drying | As recommended for the Glasurit clear used. | |

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(e)(840)839: The EU limit value for this product (product category: IIB.e) in ready to use form is max 840 g/litre of VOC. The VOC content of this product is 839 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

