

Glasurit® Blending Clear



- Application:** Glasurit® 55-B500 Blending Clear is used for blending in metallic Glasurit® 55 Line basecoats.
- Properties:** It helps to achieve a smooth homogeneous overspray area in the fade-out zone, avoiding dark shadows around the repair area.
- Remarks:**
- The spraygun can be used for 55-B500 Blending Clear and 55 Line Basecoat without having to be cleaned in between.

	Paint system	S 8 , S 8.1
	VOC ready for use	> 420 g/l
	Mixing ratio	ready for use
		Shake well before use.
	Spray viscosity DIN 4 at 20°C	17 –19 s
	Gravity cup Spraying pressure	HVLP-gravity-feed spray gun: 1.3 mm 2.0 – 3.0 bar 0.7 bar at the nozzle Compliant gravity-feed spray gun: 1.3 -1.4 mm 2.0 bar
	Number of spraycoats	1 wet coat
	Flash-off at 20°C	none

Safety advice:

The products are suitable for professional use only.
It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

