55-B500





Application:

Glasurit 55-B500 Blending Clear is used for blending in metallic Glasurit 55 Line basecoats.

Key Features:

It helps to achieve a smooth homogeneous overspray area in the fade-out zone, avoiding dark shadows

around the repair area.

Remarks:

 The spraygun can be used for 55-B500 Blending Clear and 55 Line Basecoat without having to be cleaned in between.



Mixing Ratio

Ready for use

Shake well before use.



Spray viscosity at 20°C

17-19 s

DIN 4:

Potlife at 20°C

Application:		Compliant gravity-feed spray gun	HVLP spray gun
Application pressure	bar	2	2-3
Nozzle pressure	bar		0.7
Nozzle size		1.3-1.4	1.3
Number of spray coats		1 wet coat	

Flash off at 20°C min none

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < $0.1 \mu m$.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.