

Glasurit® plastic additive



- Application:** Additive which makes Glasurit Non-Sanding-Filler suitable for direct application to all paintable plastic substrates normally used in the automotive industry.
- Properties:** good miscibility
- Remarks:**
- No addition for painting of GRP necessary
 - The product can also be applied to adjacent e-coated new parts, if necessary.
 - The addition of 522-10 does not produce adhesion to unpaintable pure polypropylene (PP) and polyethylene (PE)

	Paint system	S 3	
	Mixing ratio	3 : 1 : 1 100% by vol.	285-31, -38, -49, -95, -0
	Hardener	33% by vol.	929-56, -55
	Reducer	33% by vol.	522-10
	Spray viscosity DIN 4 at 20°C	14 – 20 s	Potlife at 20°C 1 – 2 hours
	Gravity cup Spraying pressure	HVLP-gravity-feed spray gun: 1,3 mm 2,0 – 3,0 bar / 0,7 bar at the nozzle	Compliant gravity-feed spray gun: 1,3 – 1,4 mm 2,0 bar
	Number of spraycoats	½ + 1 (body filled area / entire surface) Film thickness: 20 – 35 µm	2 Film thickness: 40 – 60 µm
	Flash-off at 20°C	15 – 20 min.	-
	Drying at 60 °C	-	25 Min.
	Sanding: manual	-	P500 - P800
	Sanding: orbital sander	-	P400 - P500

Safety advice:

The products are suitable for professional use only.
It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

