

Hardeners / activators for undercoats

Body Fillers		948-22	948-36 / -52
839-20/20K	Glasurit® Multi Purpose Body Filler		●
839-25	Glasurit® Fine Body Filler		●
839-55	Glasurit® Soft-Body Filler		●
839-70/70K	Glasurit® Universal Body Filler		●
839-85	Glasurit® Multi Brushing Body Filler		●
839-90	Glasurit® Plastic Body Filler		●
901-21	Glasurit® Glass fibre body filler		●
1006-26	Glasurit® UP-Spray Filler grey	●	

Primers		352-230	929-26
283-150	Glasurit® Etch Primer Filler	●	
285-26	Glasurit® 2K SF Primer		●

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



Hardeners / activators for undercoats

Primer Fillers		352-228	929-55	929-56	929-58	965-60	93-E3
283-150	Glasurit® Etch Primer Filler	●					
285-230	Glasurit® Primer Filler Pro, white				●		
285-270	Glasurit® Primer Filler Pro, grey				●		
285-290	Glasurit® Primer Filler Pro, black				●		
285-505	Glasurit® HS Primer Filler, grey		●	1			
285-555	Glasurit® HS Primer Filler, black		●	1			
285-655	Glasurit® HS Primer Filler, white		●	1			
285-700	Glasurit® Primer Filler		●	1			
285-730	Glasurit® Primer Filler, white		●	1			
285-790	Glasurit® Primer Filler, black		●	1			
801-72	Glasurit® Epoxy Primer Filler grey					●	
934-70	Glasurit® 2K Plastic Primer Filler			●			
176-72	Glasurit® 1K Primer Filler						●

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



Hardeners / activators for undercoats

Fillers and Surfacer		929-55	929-56
285-0	Glasurit® HS Transparent Sealer	2	●
285-31	Glasurit® HS VOC Non-Sanding Filler, light grey	2	●
285-38	Glasurit® HS VOC Non-Sanding Filler, white	2	●
285-49	Glasurit® HS VOC Non-Sanding Filler, black	2	●
285-95	Glasurit® HS VOC Tintable Filler, transparent	●	●

not applicable

possible undercoat / hardener or activator combinations

1 for large areas and rather high application temperatures

2 for small areas and rather low application temperatures

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

