

### Temperature table

Which hardeners and which reducers should be used in 2K PU topcoat and in clears?

The material combination (hardener and reducer) may be changed depending on temperature and object size. The hardeners and reducers recommended below for the various temperature ranges are for overall resprays. For panel repairs, select the material combination indicated for the next lower temperature range.

**Please also respect the latest technical information sheets!**

	Glasurit® 923-625, -630, -645	Glasurit® 923-610
	3:1:1	3:1:1
<b>Spray viscosity DIN 4 / 20°C</b>	<b>18 - 21 s</b>	<b>18 - 21 s</b>
<b>from 15°C</b>	929-61 352-10 352-30	929-61 352-10
<b>from 20°C</b>	929-63 352-30 352-40	929-61 352-10 352-30
<b>from 25°C</b>	929-63 352-40	929-61 352-30
<b>from 30°C</b>	929-64 352-40	929-63 352-40

#### Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at <http://techinfo.glasurit.com> or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

