100-M 10

100 Line Basecoat Variant Interior



Application:		Variant for Interior finish		
	Paint System	Please see Glasurit Know How module "INTERIOR COLOR PROCESS – 100 Line".		
		100:10:50		
	Mixing Ratio	100 % by weight	100- Metallic (incl. 100-M 10 according to mixing formula)	
	Hardener	10 % by weight	100-IC 550	
	Reducer	50 % by weight	100-IC 660 Stir IMMEDIATELY after adding 100-IC 550 Interior additive and 100-IC 660 Interior reducer.	

Application:		spray gun	₩ HVLP spray gun	
Application pressure	bar	2		
Nozzle size		1.3-1.4		
Number of spraycoats		1 full coat + 1 "Finish coat" applied wet-on-wet		
Flash-off at 20°C min		5 min flash-off after the "Finish coat"		
Film thickness	μm	10-15		
Application Remark		Spraying pressure = inlet pre The setup depends on the spray gun supplier, please refer to		

Compliant gravity-feed

KNOWLEDGE – BODYSHOP EQUIPMENT" for detailed information.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < $0.1 \mu m$.

2004/42/IIB(d)(420)249: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 249 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

100-M 10

100 Line Basecoat Variant Interior





Drying at 60 °C

20 min after flash off

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 $\mu m.$

2004/42/IIB(d)(420)249: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 249 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH - Automotive Refinish Coatings Solutions Europe - Glasuritstrasse 1 - 48165 Münster - Germany